

5ER-O17: ผลของความเข้มข้นของโซเดียมไฮดรอกไซด์ต่อคุณสมบัติของ จีโอโพลิเมอร์มอร์ตาร์เสริมเส้นใยบะซอลต์

Effect of Sodium Hydroxide Concentration on Properties of Basalt Fiber Reinforced Geopolymer Mortar

วันโชค เครือหงษ์¹ ทศพร ประเสริฐศรี^{1*} พชร เครือวิทย์²
ชิสณพงศ์ สุธัมมะ³ ศตวรรษ หฤหรรษ์พงศ์¹ และ รัชญา ยอดดำรงค์¹

Wunchock Kroehong¹, Tosporn Prasertsri^{1*}, Pochara Kruavit²

Chisanuphong Suthumma³, Sattawat Haruehansapong¹ and Pruchaya Yoddumrong¹

บทคัดย่อ

งานวิจัยนี้ว่าด้วยการเพิ่มความเข้มข้นของสารละลายโซเดียมไฮดรอกไซด์เพื่อศึกษาคุณสมบัติของตัวอย่างจีโอโพลิเมอร์มอร์ตาร์เสริมเส้นใยบะซอลต์ ส่วนเชื่อมประสานของจีโอโพลิเมอร์จัดเตรียมขึ้นจากปูนซีเมนต์ปอร์ตแลนด์ธรรมดา โซเดียมไฮดรอกไซด์ และโซเดียมซิลิเกต ทุกส่วนผสมน้ำต่อซีเมนต์และอัตราส่วนเส้นใยต่อซีเมนต์ (โดยน้ำหนัก) เท่ากับ 0.6 และ 1.0 ตามลำดับ สารละลายโซเดียมไฮดรอกไซด์ที่มีความเข้มข้น 8 12 และ 16 โมลาร์ถูกใช้เป็นตัวเร่งปฏิกิริยา นอกจากนี้ผลของการใช้อัตราส่วนน้ำหนักระหว่างโซเดียมไฮดรอกไซด์และโซเดียมซิลิเกตด้วยค่าที่ต่างกันได้รับการพิจารณาด้วย ข้อมูลที่ทำการตรวจวัดประกอบด้วยความชื้นเหลว ระยะเวลาก่อตัว กำลังรับแรงอัดประลัย และความหนาแน่นรวมของตัวอย่างทดสอบ จากผลทดสอบพบว่า การเพิ่มความเข้มข้นของสารละลายโซเดียมไฮดรอกไซด์ส่งผลให้ความชื้นเหลวและระยะเวลาก่อตัวของตัวอย่างทดสอบลดลง กำลังอัดประลัยของตัวอย่างทดสอบที่อายุ 28 วันมีค่าเพิ่มขึ้นจากการเพิ่มอัตราส่วนน้ำหนักระหว่างโซเดียมไฮดรอกไซด์และโซเดียมซิลิเกต อย่างไรก็ตาม ผลทดสอบบ่งชี้ว่าความเข้มข้นของสารละลายโซเดียมไฮดรอกไซด์ไม่ก่อให้เกิดความแตกต่างที่ชัดเจนของความหนาแน่นรวมของตัวอย่างทดสอบ

คำสำคัญ: เส้นใยบะซอลต์ จีโอโพลิเมอร์ ความเข้มข้นของโซเดียมไฮดรอกไซด์

Abstract

This research deals with increasing concentration of sodium hydroxide solution to investigate various properties of a basalt fiber reinforced geopolymer mortar specimen. The geopolymer binder was produced using ordinary Portland cement, sodium hydroxide, and sodium silicate. For all mixtures, the water-to-cement ratio and the fiber-to-cement ratio (by weight) were kept constant at 0.6 and 1.0, respectively. Sodium hydroxide solution was introduced as an alkaline activator at a molar concentration of 8, 12, and 16. Additionally, the effect of different weight ratio between sodium hydroxide and sodium silicate had been evaluated. The measured data consisted of consistency, setting time, compressive strength, and bulk density of the tested specimens. The results showed that the increase of sodium hydroxide solution caused a reduction in consistency and setting times of specimen. The 28-day compressive strength of specimen increased as the weight ratio between sodium hydroxide and sodium silicate increased. However, there had no detrimental effect for the bulk modulus of the specimens with different sodium hydroxide solution concentration.

Keywords: Basalt fiber, Geopolymer, Sodium Hydroxide Concentration

¹ คณะวิศวกรรมศาสตร์และสถาปัตยกรรมศาสตร์ มหาวิทยาลัยเทคโนโลยีราชมงคลตะวันออก

¹ Faculty of Engineering and Architecture, Rajamangala University of Technology Tawan-ok

² คณะวิศวกรรมศาสตร์ จุฬาลงกรณ์มหาวิทยาลัย

² Faculty of Engineering, Chulalongkorn University

³ คณะวิศวกรรมศาสตร์ กำแพงแสน มหาวิทยาลัยเกษตรศาสตร์ วิทยาเขตกำแพงแสน นครปฐม

³ Faculty of Engineering at Kamphaengsaen, Kasetsart University KPS Campus, Nakhon Pathom

* Corresponding author. E-mail: tosporn_pr@rmutto.ac.th

Introduction

The production of Portland cement continuously contributes to large amount of global CO₂ emission (Parveen et al., 2018; Rahmiati et al., 2015; Scrivener and Kirkpatrick, 2008; Turner and Collins, 2013). This is the crucial reason for developing low-energy materials to reduce environmental problems and CO₂ emissions and make the most of by-products, resulting in a new development approach. One example is developing geopolymers materials, a new alternative binder to replace concrete, using powdery materials containing high silica (Si) and Alumina (Al) to react with strong bases. It is often a large by-product of industrial manufacturing processes. The development of a geopolymer is one attempt to reduce energy consumption to reduce the use of ordinary Portland cement (OPC) and clinker, and it also brings out a large amount of waste material. A development of geopolymer began using the chemical reaction of Si-Al-containing elements in a mature alkaline state through a polycondensation process (Davidovits, 1994). Geopolymers is different to conventional concrete since the formation of calcium-based system, known as calcium silicate hydrate system, will not produce. An amorphous microstructure formed by aluminum-silicon compound. The non-crystalline structure of hardened geopolymer concrete is stabilized to resist various environmental conditions and loading due to serviceability. According to the present research on geopolymer research, by-products of various industries have been introduced, and the use of reinforced fibers in concrete has become increasingly popular. In this research, basalt fiber (BF) was selected to be used in the development of geopolymer mortar.

The use of fiber reinforcement has great potential to enhance various properties of geopolymer mortars. The literature has been focused on different type of fibers, e.g. basalt (Punurai et al., 2018; Saloni et al., 2020), glass (Al-Majidi et al., 2017; Alomayri, 2017; Bhutta et al., 2018; Goncalves and Bindiganavile, 2018), steel (Faris et al., 2016; Farhan et al., 2018; Ma et al., 2019b; Onuaguluchi et al., 2017), and synthetic materials (Behfarnia and Rostami, 2017; Nguyen et al., 2018a; Nguyen et al., 2018b; Noushini et al., 2018). Basalt fiber is selected as the reinforcing particle of geopolymer mortars tested in this research. The reason of this choice is due to an improvement of strength and setting time of mortars. The total porosity, drying shrinkage, and critical pore size were also reduced (Punurai et al., 2018; Saloni et al., 2020). Some basalt fiber geopolymer materials have been studied from previous research, but few studies have been done. Therefore, in this research, further studies are being carried out to develop geopolymer materials by replacing basalt fibers for further improvement by adjusting the sodium hydroxide (NH) to sodium silicate ratio (NS) ratio. This research focuses on various properties, such as consistency, setting time, compressive strength, and bulk density of geopolymer mortars. To be useful research information for those who are interested in developing new materials to replace old materials and to use in the development of building materials for the construction industry.

This research presents an experimental study to evaluate the significance of increasing both sodium hydroxide (NH) concentration and NH to sodium silicate (NS) ratio to a basalt fiber reinforced geopolymer mortar specimen. The properties of fresh pastes and hardened mortars are examined. Experimentations to determine durability and microstructural properties are beyond the scope of this work.

Experimental Program

The chemical compositions of OPC and BF are presented in Table 1. The cement and fiber used in this research were identical to those in the literature (Soeurt and Chalee, 2017; Punurai et al., 2018). OPC, used for all mixtures, conformed to the requirements of Portland cement standard (ASTM, 2020). Natural river sand, which have a specific gravity of 2.5, was utilized as fine aggregate. BF used was classified as alkaline basalt, since silicon dioxide content is less than 42%. The combination of NH and NS solutions were used for the alkaline activation of geopolymer mortar.

Table 1 Chemical analysis of OPC and BF.


Compound (%)	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	CaO	MgO	Na ₂ O	K ₂ O	SO ₃	LOI
OPC	20.10	5.20	3.15	60.24	1.13	0.11	0.43	2.42	2.03
BF	32.80	13.20	0.81	31.30	6.39	0.46	0.42	0.67	0.45

The total mass of OPC and fine aggregate, applied to each mixture, was 650 and 650 kg/m³, respectively. Free water to OPC ratio was kept at 0.6. The basalt fiber content used was 100% by weight to minimize the porosity of geopolymer mortar as suggested in the literature (Punurai et al., 2018). The constituent activators in the geopolymer mortars are summarized in Table 1. NH, that is offered in solid pellet form and conformed to the requirements of NH standard (TIS, 2006), was solved in distilled water. NH solutions were prepared separately, at concentrations of 8, 12, and 16 mol, and mixed with aqueous NS solution. The specimens were designated according to the NH / NS ratio by weight and NH concentration. The NH / NS ratio was set to 1, 1.5, and 2 for the S1, S2, and S3, respectively. The amount of NH solutions (in kg/m³) for each mixture did not keep constant because the total quantity of NH and NS solutions was set as 390 kg/m³ to control the level of alkaline solution in geopolymer pastes. Effects of variation of NS solutions with constant NH solutions on properties of geopolymer concrete are recommended for further evaluation.

Table 2 Mixture proportion of geopolymer mortars.

Specimen	S1-8M	S1-12M	S1-16M	S2-8M	S2-12M	S2-16M	S3-8M	S3-12M	S3-16M
NH (mol)	8	8	8	12	12	12	16	16	16
NH (kg/m ³)	195	234	260	195	234	260	195	234	260
NS (kg/m ³)	195	156	130	195	156	130	195	156	130

Generally, mixing water with strong bases is considered as exothermic reaction, which may generate significant amount of heat. To prevent a vigorous exothermic reaction, NH in aqueous solution was rested for 24 hours before mixing with NS solution. The alkaline solution, obtained from a combination of NH in aqueous solution and NS solution, was then mixed with other components. OPC, BF, fine aggregate, and alkaline solution were blended under a dry condition for 5 minutes. The well-blended mixture was obtained as demonstrated in Figure 1(a). The basalt fiber reinforced geopolymer pastes were casted, shown in Figure 1(b), using acrylic prism mold with a size of 50 × 50 × 50 mm. After 24 hours, the hardened mixtures were demolded and further cured with plastic sheeting for 7 or 28 days. The curing process of mortars are captured in Figure 1(c).

**Figure 1** Specimen preparation.

Fresh mortar mixture was then examined for its consistency using flow table test as seen in figure 2(a). The procedure was based on the standard testing (ASTM, 2015), which is widely applied in the previous studies (Huseien et al., 2018; Lu & Poon, 2018; Pangdaeng et al., 2014). The Vicat apparatus according to the specification (ASTM, 2019), as depicted in Figure 2(b), was applied to measure a penetration resistance in terms of initial and final setting time of mortars. The compressive strength of specimens was determined by the test shown in Figure 2(c), as per the standard (ASTM, 2005), at 7 and 28 days using 50 × 50 × 50 mm cubes.

A constant loading rate of 0.5 MPa per second was applied to the specimens until crushing failure occurred. A failure load value divided by a cross-sectional area of specimen is evaluated as the compressive strengths of geopolymer mortars.

Results and Discussions

The experiment yielded a number of results associated with various properties in both fresh and hardened state of the specimens. The flow percentage, as reported in Figure 3(a), was pursued to achieve the rheological property of geopolymer mortars. A similar trend could be identified for all mixture that the flowability decreased with increasing NH concentration. Rates of change of flow percentage increased as the increasing amount of NH concentration, except for the case with NH / NS ratio of 1.5. These identical trends could be also obtained while determining the rate of change by setting NH / NS ratio as a control parameter. Even though the case with NH / NS ratio of 1.5 had made remarkable rate of change of flow percentage, the results also suggested that increasing NH / NS ratio will reduce flowability of fresh mixture of the geopolymer pastes.



(a) Standard flow test



(b) Penetration resistance test



(c) Uniaxial compressive test

Figure 2 Geopolymer mortar testing.




Figure 3 Effect of solution concentration on workability of geopolymer pastes.

The results of setting times were shown in Figure 3(b). The hatched bars and the non-hatched bars indicate the initial setting time and the final setting time of geopolymer mortars, respectively. The samples which were increasing the NH / NS ratio from containing different concentration of NH. It is shown that the NH / NS ratio can cause urgent of setting times. Higher concentration of NH leads to longer setting times. The reasons are similar to those described for flowability finding. According to the results plotted in Figure 4(a), the hatched bars and the non-hatched bars represent the compressive strength of mortar at 7 days and 28 days, respectively. The 28-day compressive strength of samples containing high concentration of NH are not slightly different of the lower but It is obvious that higher proportion of NH / NS causes increase in compressive strength,




Figure 4 Effect of solution concentration on physical properties of mortar specimens.

The bulk density of sample, depicted in Figure 4(b), which study the concentration of NH that may not always be able to effect of density, because of mixture proportion of geopolymer mortars were measured and equal in weight ratio. However, a limited number of geopolymer mortar specimens could lead to a lower generalization of the current results. Further research should be extended to determine the optimal amount of NH concentration, which can effectively improve both strength and workability, for basalt fiber reinforced geopolymer mortars.

Conclusions

This research experimentally investigated the geopolymer mortar specimens to evaluate the effect of NH Concentration on consistency, setting time, compressive strength, and bulk density of the tested specimens. Based on the test results, the following conclusions are drawn:

- The decrease in flowability was more pronounced with the increase in NH concentration. Furthermore, the flow percentage of the pastes was also reduced as the NH / NS ratio improved.
- Increasing the NH / NS ratio from containing different concentration of NH and NH / NS ratio can cause urgent of setting times
- It is obvious that higher proportion of NH / NS ratio causes increase in compressive strength.
- The concentration of NH that may not always be able to effect of density.

Acknowledgement

The authors acknowledge the facility supports and research funding from the Faculty of Engineering and Architecture, Rajamangala University of Technology, Tawan-ok, Thailand.

References

- Al-Majidi, M.H., Lampropoulos, A., and Cundy, A.B. (2017). Tensile properties of a novel fibre reinforced geopolymer composite with enhanced strain hardening characteristics. *Composite Structures*. 168, 402-427.
- Alomayri, T. (2017). Effect of glass microfibre addition on the mechanical performances of fly ash-based geopolymer composites. *Journal of Asian Ceramic Societies*. 5(3), 334-340.
- American Society of Testing Materials (ASTM). (2015). Standard test method for flow of hydraulic cement mortar (ASTM C1437-15). Pennsylvania, The United States.
- American Society of Testing Materials (ASTM). (2019). Standard test methods for time of setting of hydraulic cement by Vicat needle (ASTM C191-19). Pennsylvania, The United States.
- American Society of Testing Materials (ASTM). (2020). Standard specification for portland cement (ASTM C150 / C150M-20). Pennsylvania, The United States.
- American Society of Testing Materials (ASTM). (2005). Standard test method for compressive strength of hydraulic cement mortars (ASTM C109 / C109M-05). Pennsylvania, The United States.

- Behfarnia, K. and Rostami, M. (2017). Mechanical properties and durability of fiber reinforced alkali activated slag concrete. *Journal of Materials in Civil Engineering*. 29(12), 04017231.
- Bhutta, A., Farooq, M., Borges, P.H.R., and Banthia, N. (2018). Influence of fiber inclination angle on bond-slip behavior of different alkaliactivated composites under dynamic and quasi-static loadings. *Cement and Concrete Research*. 107, 236-246.
- Davidovits, J. (1994). Geopolymers: Man-made rock geosynthesis and the resulting development of very early high strength cement. *Journal of Materials Education*. 16, 91-139.
- Fang, G., Ho, W.K., Tu, W., and Zhang, M. (2018). Workability and mechanical properties of alkali-activated fly ash-slag concrete cured at ambient temperature. *Construction and Building Materials*. 172, 476-487.
- Faris, M.A., Abdullah, M.M A.B., Ismail, K.N., Muniandy, R., and Jaya, R.P. (2016). Performance of straight steel fibres reinforced alkali activated concrete. *IOP Conference Series: Materials Science and Engineering*. 133, 012045.
- Goncalves, J.R.A. and Bindiganavile, Y.B.V. (2018). Thermal properties of fibre reinforced alkali-activated concrete in extreme temperatures. *Magazine of Concrete Research*. 70(18), 954-964.
- Huseien, G.F., Mirza, J., Ismail, M., Ghoshal, S.K., and Ariffin, M.A.M. (2018). Effect of metakaolin replaced granulated blast furnace slag on fresh and early strength properties of geopolymer mortar. *Ain Shams Engineering Journal*. 9(4), 1557-1566.
- Lu, J.X. and Poon, C.S. (2018). Use of waste glass in alkali activated cement mortar. *Construction and Building Materials*. 160, 399-407.
- Ma, G., Li, Z., Wang, L., and Bai, G. (2019). Micro-cable reinforced geopolymer composite for extrusion-based 3D printing. *Materials Letters*. 235(1), 144-147.
- Nguyen, H., Carvelli, V., Adesanya, E., Kinnunen, P., and Illikainen, M. (2018a). High performance cementitious composite from alkaliactivated ladle slag reinforced with polypropylene fibers. *Cement and Concrete Composites*. 90(7), 150-160.
- Nguyen, H.H., Choi, J.I., Song, K.I., Song, J.K., Huh, J., and Lee, B.Y. (2018b). Self-healing properties of cement-based and alkaliactivated slag-based fiber-reinforced composites. *Construction and Building Materials*. 165, 801-811.
- Noushini, A., Hastings, M., Castel, A., and Aslani, F. (2018). Mechanical and flexural performance of synthetic fibre reinforced geopolymer concrete. *Construction and Building Materials*. 186(10), 454-475.
- Onuaguluchi, O., Borges, P.H.R., Bhutta, A., and Banthia, N. (2017). Performance of scrap tire steel fibers in OPC and alkali-activated mortars. *Materials and Structures*. 50(2), 157.
- Pangdaeng, S., Phoo-ngernkham, T., Sata, V., and Chindaprasirt, P. (2014). Influence of curing conditions on properties of high calcium fly ash geopolymer containing Portland cement as additive. *Materials and Design*. 53, 269-274.

- Parveen, Singhal, D., Junaid, M.T., Jindal, B.B., and Mehta, A. (2018). Mechanical and microstructural properties of fly ash based geopolymer concrete incorporating alccofine at ambient curing, *Construction and Building Materials*. 180, 298–307.
- Punurai, W., Kroehong, W., Saptamongkol, A., and Chindaprasirt, P. (2018). Mechanical properties, microstructure and drying shrinkage of hybrid fly ash-basalt fiber geopolymer paste. *Construction and Building Materials*. 186(10), 62–70.
- Rahmiati, T., Azizli, K.A., Man, Z., Ismail, L., and Nuruddin, M.F. (2015). Effect of solid/liquid ratio during curing time fly ash based geopolymer on mechanical property. *Materials Science Forum*. 803, 120-124.
- Saloni, Parveen, and Pham, T.M. (2020). Enhanced properties of high-silica rice husk ash-based geopolymer paste by incorporating basalt fibers. *Construction and Building Materials*. 245, 118422.
- Scrivener, K.L. and Kirkpatrick, R.J. (2008). Innovation in use and research on cementitious material. *Cement and Concrete Research*. 38(2), 128–136.
- Soeurt, R. and Chalee, W. (2017). The influence of NaOH concentration on compressive strength of fly ash concrete. *The Journal of KMUTNB*. 27(4), 737-749.
- Thai Industrial Standard (TIS). (2006). Sodium hydroxide for industrial uses (TIS 150-2549). Bangkok, Thailand.
- Turner, L.K. and Collins, F.G. (2013). Carbon dioxide equivalent (CO₂-e) emissions: a comparison between geopolymer and OPC cement concrete. *Construction and Building Materials*. 43, 125–130.